



R6200 EVA LAMINATING ADHESIVE

PRODUCT DESCRIPTION

R6200 is a high performance EVA based laminating adhesive, designed to bond a variety of vinyls and fabrics to porous substrates such as MDF, particle board, plywood and plasterboard, etc.. It develops rapid wet tack and dries to a clear, tough, flexible bond.

It is also used as a versatile paper converting adhesive for coated papers and boards, and is most suitable for packet making. The dry film is suitable for indirect contact with dry foodstuffs.

SURFACE PREPARATION.

Surfaces to be bonded should be clean, dry and free from dust and oil. Edges should be squarely machined to insure maximum contact.

TYPICAL PROPERTIES

<i>Appearance</i>	<i>White liquid</i>
<i>Dry Film</i>	<i>Tough, clear and flexible</i>
<i>Base</i>	<i>Synthetic Emulsion</i>
<i>Solids</i>	<i>55%</i>
<i>Viscosity</i>	<i>3000 cps 4/20/25°C</i>
<i>Clean Up</i>	<i>Warm soapy water</i>
<i>Shelf Life</i>	<i>Up to 12 months in sealed plastic containers at 20°C</i>
<i>Packaging</i>	<i>20lt. 200lt. 1000lt tanks..</i>

THIS PRODUCT IS LOW IN TOXICITY

APPLICATION

R6200 may be applied by squeeze bottle, brush or roller. Bonds should be assembled within 2 - 3 minutes and then tightly clamped or pressed until the adhesive has set. Wipe off adhesive squeeze out immediately after assembly with a dry or slightly damp cloth.

Assemblies should be clamped for 2 - 4 hours and are best left overnight before moving or transportation. Maximum bond strength is achieved within 48 hours.

R6200 should be used as supplied.

SAFETY DIRECTIONS

Storage

For optimum shelf life store in tightly closed, original containers out of direct sunlight between 15 and 25°C. Do not freeze.

Disposal

Please dispose of empty containers and residue in accordance with your local waste management regulations.

First Aid

In use, please ensure that Occupational Health and Safety requirements are observed.

Eyes: Irrigate with water for 10 minutes and see a doctor.

Skin: Wash off with warm water and soap

If swallowed, give plenty of water. Do not induce vomiting. Seek medical attention.

Material Safety Data Sheet available upon request

Issued: March 2007

The application, use and processing of our products is the responsibility of the user. Any technical or other advice, information or data provided by us, whether verbally, in writing or by way of trials or tests, is given without guarantee or warranty. Refer to Material Safety Data Sheets for information on Storage & Handling, Health and Safety, and Transport.

RLA POLYMERS PTY LTD

ACN 004 709 915

215 Colchester Road, Kilsyth, Victoria 3137 Australia
P.O. Box 147, Kilsyth, Victoria 3137 Australia
Telephone: (03) 9728 1644 • Facsimile: (03) 9728 6009
E-mail: info@rlapolymers.com.au

 A British Vita Group Company



67 Dalgety Drive (P.O. Box 97-575)
Manukau City, Auckland, New Zealand
Telephone: (9) 268 0301
Facsimile: (9) 268 0305

RLA 0448